



## Danafloat™ 271 mineral collector

### Application

*Danafloat 271* is an aqueous solution of dialkyl dithiophosphate and mercaptobenzothiazole.

*Danafloat 271* has little or no frothing properties. It requires a longer conditioning time than do xanthates and for this reason is usually added to a conditioning step or in some instances to the grinding mill.

*Danafloat 271* is a stronger collector than *Danafloat 371*. It is an excellent collector for tarnished or rapidly oxidizing ores, which are normally difficult-to-float ores. *Danafloat 271* has found application in the flotation of liberated gold, partly free and partly associated with pyrite and arsenopyrite. It is rated an excellent collector in the flotation of auriferous pyrite, particularly in acid circuits. The collector floats oxidized galena well, but has a quite strong effect on sphalerite and should therefore be used with great care. *Danafloat 271* should be considered as a sphalerite

collector in any screening test programme. It is also an excellent collector in the flotation of copper and nickel. In many instances a scavenger collector, e.g. xanthate, is used for optimum recovery. *Danafloat 271* should be considered as co-collector in the flotation of copper ores, particularly if part of the copper is oxidized or tarnished.

*Danafloat 271* can be added undiluted or preferably diluted with clear water to 5-20% solutions. It is good practice to stir before use.

The dosage of *Danafloat 271* varies with the type of ore, usually falling in the range of 10 to 100 grams per metric ton ore.

Experience has shown that *Danafloat 271* is effective in the pH range of 3-12.

### Composition

Chemical name:	i-butyl-dtp-Na and MBTNa
CAS name:	Phosphorodithioic acid, O,O-bis(2-methyl-propyl)ester, sodium salt and 2(3H)-Benzothiazolethione, sodium salt
Active ingredient:	10-12% and 21-24% by weight respectively

### Physical properties

Appearance:	Yellow to brown
Form:	Liquid (aqueous solution)
Boiling point:	-
Melting/freezing point:	-
Specific gravity:	1.14 g/ml
Flash point:	Above 65 degrees C



**CHEMINOVA A/S**

P.O. Box 9  
DK-7620 Lemvig  
Denmark  
Phone +45 96 90 96 90  
Fax +45 96 90 96 91  
[danafloat.com](http://danafloat.com)

**Safety and handling**

*Danafloat* flotation collectors are manufactured under carefully controlled conditions. However, to varying degrees they can be considered harmful and therefore before handling this product always carefully read and understand the MSDS for this product.

*Danafloat 271* causes irritation to eyes and skin.

Safe handling includes the use of safety glasses, natural rubber gloves and protective clothing.

**Storage**

- + Store in a dry and well-ventilated place away from heat and sunlight after the principle "first in/first out"
- + Avoid freezing
- + Store in plastic drums or coated steel drums

**Environmental impact**

*Danafloat 271* is biodegradable. LC<sub>50</sub>, 96 hrs Rainbow trout 1.8 mg/l for MBTNa. LC<sub>50</sub>, 48 hrs Daphnia magna 19 mg/l for MBTNa. The majority of the collector is tied up with the concen-

trate and is destroyed in subsequent processing operations. The remainder is transferred to the tailings. Release into the water systems should be avoided.

**Packing**

*Danafloat* mineral collectors are supplied in tank containers or plastic drums. If preferred, *Danafloat* collectors may be supplied in coated steel drums.

Tank containers	Net weight:	approx. 20 mt
Drums	Net weight:	225 kg
	Gross weight:	approx. 235.5 kg for plastic drums approx. 247 kg for coated steel drums

Notice to customer: The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Cheminova A/S 2011