



## Danafloat™ 507 B mineral collector

### Application

*Danafloat 507 B* is an aqueous solution of dialkyl dithiophosphate, thionocarbamate and iso-butanol.

*Danafloat 507 B* is normally added to the grinding circuit or in a conditioner and it has less frothing properties than *Danafloat 507*.

*Danafloat 507 B* offers good selectivity of mineral over pyrite and has been used in applications involving chalcopyrite, bornite, chalcocite and covellite copper ores. It has also found use in a mixed oxide-sulphide copper ore in conjunction with xanthate. Other applications are in the flotation of galena and Cu-activated sphalerite. *Danafloat 507 B* is a good collector for tetrahedrite.

*Danafloat 507 B* is a very fast and quite powerful collector and it should be used in smaller quantities than xanthate.

*Danafloat 507 B* should be added undiluted.

The dosage of *Danafloat 507 B* varies with the type of ore, but is normally lower than for xanthates. Recommended dosage is between 10 and 50 grams per metric ton ore.

*Danafloat 507 B* is normally used in the pH range from 4 to 12.

### Composition

Chemical name:	i-butyl-dtp-Na, thionocarbamate and iso-butanol
CAS name:	Phosphorodithioic acid, O,O-bis(2-methyl propyl)ester, sodium salt and O-Isopropylethylthionocarbamate, 2-methyl (-1-propanol)
Active ingredient:	32-35 % and 28-31% and 3.6-4.4% by weight respectively

### Physical properties

Appearance:	Light brown
Form:	Liquid (aqueous solution)
Boiling point:	102.5 degrees C
Melting/freezing point:	Minus 5 to minus 7 degrees C
Specific gravity:	1.07 g/ml
Flash point:	None



CHEMINOVA  
**DANAFLOAT™**



#### **CHEMINOVA A/S**

P.O. Box 9  
DK-7620 Lemvig  
Denmark  
Phone +45 96 90 96 90  
Fax +45 96 90 96 91  
[danafloat.com](http://danafloat.com)

### **Safety and handling**

*Danafloat* collectors are manufactured under carefully controlled conditions. However, to varying degrees they can be considered harmful and therefore before handling this product always carefully read and understand the MSDS for this product.

*Danafloat 507 B* is harmful if swallowed and causes irritation to eyes and skin.

Safe handling includes the use of safety glasses, natural rubber gloves and protective clothing. Additionally, avoid inhalation of vapours.

### **Storage**

- + Store in a dry and well-ventilated place away from heat and sunlight after the principle "first in/first out"
- + Avoid freezing
- + Store in plastic drums or coated steel drums

### **Environmental impact**

*Danafloat 507 B* is biodegradable. The majority of the collector is tied up with the concentrate and is destroyed in the subsequent

processing operations. The remainder is transferred to the tailings. Release into the water systems should be avoided.

### **Packing**

*Danafloat* mineral collectors are supplied in tank containers or plastic drums. If preferred, *Danafloat* collectors may be supplied in coated steel drums.

Tank containers	Net weight:	approx. 20 mt
IBC containers	Net weight:	1,000-1,075 kg
	Gross weight:	approx. 1,059-1,134 kg
Drums	Net weight:	225 kg
	Gross weight:	approx. 235.5 kg for plastic drums approx. 247 kg for coated steel drums

Notice to customer: The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Cheminova A/S 2011



**CHEMINOVA**  
**DANAFLOAT™**